



SCHEDA TECNICA – DATA SHEET - DATENBLATT – FICHE TECHNIQUE

| | |
|---|--|
| Articolo/Article/Artikel/Article | RIPLEY |
| Altezza/Width/Breite/Largeur | 140 cm |
| Composizione/Composition/Zusammensetzung/Composition | 31% Recycled CO – 22% Recycled WO 21% PC – 16% PL – 10% SE |
| Peso/Weight/Gewicht/Poids | 535g/sqm - 750g/lm |
| Prodotta in/Made in/Hergestellt in/Fabriqué en | Italia/Italy/Italien/Italie |
| Tariffa doganale/Custom tariff/Zolltarif/Tarif douaniere | 55152900 |
| | |
| Resistenza all'abrasione/Abrasion resistance/Scheuerfestigkeit/Résistance à l'abrasion (UNI EN ISO 12947-2 / Martindale) | 70.000 rubs |
| Pilling (5.000 cicli)/Pilling (5.000 rubs)Pilling (5.000 scheuertouren)/Pilling (5.000 tours) (UNI EN ISO 12945-2) | 3/4 |
| Solidità del colore alla luce/Lightfastness/Lichtechtheit/Solidité à la lumière (UNI EN ISO 105 B02 / Xenotest) | 4/5 |
| Solidità del colore allo sfregamento/Fastness to rubbing/Reibechtheit / Solidité au frottement (UNI EN ISO 105 X12) | secco/dry/trocken/sec 4/5 umido/wet/nass/humide 4 |
| Resistenza alla cucitura/Seam slippage/Nahtschiebewidertand/Glisement à la couture (UNI EN ISO 13936) | pass |
| Resistenza alla lacerazione/Tear strength/Weiterreissfestigkeit/Force de déchirure (UNI EN ISO 13937) | pass |
| Restringimento/Shrinkage/Schrumpfung/Rétrécissement (trama/ordito)(warp and weft)(schuss/kette)(trame/chaîne) | +/- 2% |

NORME MANUTENZIONE/CARE INSTRUCTIONS PFLEGEBEHANDLUNG/INSTRUCTIONS D'ENTRETIEN



FIRE RETARDANCY

| | | |
|----------------|------------------------------|-------------|
| Cigarette test | (EN 1021-1) (BS 5852 ign. 0) | pass |
| Match test | (EN 1021-2) (BS 5852 ign. 1) | |
| Classe 1IM | (UNI 9175/1987) | |
| Crib 5 | (BS 5852 PART IGN. 5) | |