

Articolo/Article/Artikel/Article	JAAK
Altezza/Width/Breite/Largeur	150 cm
Composizione/Composition/Zusammensetzung/Composition	90%WV – 10%PL
Peso/Weight/Gewicht/Poids	1.085 gr/m ² – 1.630 gr/lm
Spessore/Thickness/ Épaisseur/Dicke	6,5 mm (Jaak)
Prodotta in/Made in/Hergestellt in/Fabriqué en	Italia/Italy/Italien/Italie
Tariffa doganale/Custom tariff/Zolltarif/Tarif douaniere	56021031

Resistenza all'abrasione/Abrasion resistance/Scheuerfestigkeit/Résistance à l'abrasion (UNI EN ISO 12947-2 / Martindale)	80.000 rubs	
Pilling (5.000 cicli)/Pilling (5.000 rubs)/Pilling (5.000 scheuertouren)/Pilling (5.000 tours) (UNI EN ISO 12945-2)	4	
Solidità del colore alla luce/Lightfastness/Lichtechtheit/Solidité à la lumière (UNI EN ISO 105 B02 / Xenotest)	4-5	
Solidità del colore allo sfregamento/Fastness to rubbing/Reibechtheit/Solidité au frottement (UNI EN ISO 105 X12)	secco/dry/trocken/sec umido/wet/nass/humide	4-5 4-5
Resistenza alla cucitura/Seam slippage/Nachtschiebewidertand/Glisement à la couture (UNI EN ISO 13936-2)	pass	
Resistenza alla lacerazione/Tear strength/Weiterreissfestigkeit/Force de déchirure (UNI EN ISO 13937-3)	pass	
Restringimento/Shrinkage/Schrumpfung/Rétrécissement (trama/ordito)(weft/warp)(schuss/kette)(trame/chaîne)	+ / - 1%	

NORME MANUTENZIONE/CARE INSTRUCTIONS
PFLGEBEHANDLUNG/INSTRUCTIONS D'ENTRETIEN



FIRE RETARDANCY

Cigarette test	(EN 1021-1) (BS 5852 ign. 0)	Pass
Match test	(EN 1021-2) (BS 5852 ign. 1)	Pass
Classe 1IM	(UNI 9175/1987)	Pass
California	(California Technical Bulletin 117 – Section 1)	Pass